


X7R Dielectric

General Specifications



X7R formulations are called “temperature stable” ceramics and fall into EIA Class II materials. X7R is the most popular of these intermediate dielectric constant materials. Its temperature variation of capacitance is within $\pm 15\%$ from -55°C to $+125^{\circ}\text{C}$. This capacitance change is non-linear.

Capacitance for X7R varies under the influence of electrical operating conditions such as voltage and frequency.

X7R dielectric chip usage covers the broad spectrum of industrial applications where known changes in capacitance due to applied voltages are acceptable.



PART NUMBER (SEE PAGE 4 FOR COMPLETE PART NUMBER EXPLANATION)

0805

Size
(L" x W")

5

Voltage
4V = 4
6.3V = 6
10V = Z
16V = Y
25V = 3
50V = 5
100V = 1
200V = 2
500V = 7

C

Dielectric
X7R = C

103

Capacitance Code (In pF)
2 Sig. Digits + Number of Zeros

M

Capacitance Tolerance
J = $\pm 5\%$ *
K = $\pm 10\%$
M = $\pm 20\%$

* $\leq 1\mu\text{F}$ only,
contact factory for additional values

A

Failure Rate
A = Not Applicable

T

Terminations
T = Plated Ni and Sn
Z = FLEXITERM®**

*Optional termination

**See FLEXITERM® X7R section

2







Packaging
2 = 7" Reel
4 = 13" Reel

Contact Factory For Multiples

A

Special Code
A = Std. Product

NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers. Contact factory for non-specified capacitance values.



X7R Dielectric

Specifications and Test Methods



Parameter/Test		X7R Specification Limits	Measuring Conditions	
Operating Temperature Range		-55°C to +125°C	Temperature Cycle Chamber	
Capacitance		Within specified tolerance		
Dissipation Factor		$\leq 10\%$ for $\geq 50V$ DC rating $\leq 12.5\%$ for 25V DC rating $\leq 12.5\%$ for $\leq 10V$ DC rating Contact Factory for DF by PN	Freq.: 1.0 kHz $\pm 10\%$ Voltage: 1.0Vrms $\pm .2V$ For Cap > 10 μ F, 0.5Vrm @ 120Hz	
Insulation Resistance		10,000M Ω or 500M Ω - μ F, whichever is less	Charge device with rated voltage for 120 \pm 5 secs @ room temp/humidity	
Dielectric Strength		No breakdown or visual defects	Charge device with 250% of rated voltage for 1-5 seconds, w/ charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.	
Resistance to Flexure Stresses	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds	
	Capacitance Variation	$\leq \pm 12\%$		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	\geq Initial Value x 0.3		
Solderability		$\geq 95\%$ of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 \pm 5°C for 5.0 \pm 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 \pm 2 hours before measuring electrical properties.	
	Capacitance Variation	$\leq \pm 7.5\%$		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Thermal Shock	Appearance	No visual defects	Step 1: -55°C \pm 2°	30 \pm 3 minutes
	Capacitance Variation	$\leq \pm 7.5\%$	Step 2: Room Temp	≤ 3 minutes
	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +125°C \pm 2°	30 \pm 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	≤ 3 minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 \pm 2 hours at room temperature	
Load Life	Appearance	No visual defects	Pre-treatment: After mounting, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure. Charge device with \geq rated voltage in test chamber set at 125°C \pm 2°C for 1000 hours (+48, -0). Pre-treatment: After remove from test chamber, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure. Contact KYOCERA AVX for datasheet of specific parts.	
	Capacitance Variation	$\leq \pm 12.5\%$		
	Dissipation Factor	\leq Initial Value x 2.0 (See Above)		
	Insulation Resistance	\geq Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
Load Humidity	Appearance	No visual defects	Pre-treatment: After mounting, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure. Store in a test chamber set at 85°C \pm 2°C/ 85% \pm 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied. Pre-treatment: After remove from test chamber, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure.	
	Capacitance Variation	$\leq \pm 12.5\%$		
	Dissipation Factor	\leq Initial Value x 2.0 (See Above)		
	Insulation Resistance	\geq Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		

X7R Dielectric Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE	0101*		0201				0402				0603						0805						1206																				
	Reflow Only		Reflow Only				Reflow/Wave				Reflow/Wave						Reflow/Wave						Reflow/Wave																				
Soldering	Paper/Embossed		All Paper				All Paper				All Paper						Paper/Embossed						Paper/Embossed																				
(L) Length	mm (in.) 0.40 ± 0.02 (0.016 ± 0.0008)		0.60 ± 0.03 (0.024 ± 0.001)				1.00 ± 0.10 (0.040 ± 0.004)				1.60 ± 0.15 (0.063 ± 0.006)						2.01 ± 0.20 (0.079 ± 0.008)						3.20 ± 0.30 (0.126 ± 0.012)																				
(W) Width	mm (in.) 0.20 ± 0.02 (0.008 ± 0.0008)		0.30 ± 0.03 (0.011 ± 0.001)				0.50 ± 0.10 (0.020 ± 0.004)				0.81 ± 0.15 (0.032 ± 0.006)						1.25 ± 0.20 (0.049 ± 0.008)						1.60 ± 0.30 (0.063 ± 0.012)																				
(t) Terminal	mm (in.) 0.10 ± 0.04 (0.004 ± 0.0016)		0.15 ± 0.05 (0.006 ± 0.002)				0.25 ± 0.15 (0.010 ± 0.006)				0.35 ± 0.15 (0.014 ± 0.006)						0.50 ± 0.25 (0.020 ± 0.010)						0.50 ± 0.25 (0.020 ± 0.010)																				
WVDC	16		6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	500					
Cap 100 101	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									G	G	N	N	N								
Cap 150 151	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									G	G	N	N	N								
220 221	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J	E	E	E	E	E	E	E	J	J	J	J	N	N	P							
330 331	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
470 471	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
680 681	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
1000 102	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
1500 152		A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
2200 222		A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
3300 332		A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
3900 392		A	A	A	A	A																																					
4700 472		A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
5600 562		A	A	A	A	A																																					
6800 682		A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
Cap 0.01 103		A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J									J	J	J	J	N	N	P						
Cap (µF) 0.012 123																																											
0.015 153							C	C	C	C	C			G	G	G	G	G	J	J	J	J									J	J	J	J	N	N	Q						
0.018 183																																											
0.022 223			A	A	A		C	C	C	C	C			G	G	G	G	G	J	J	J	J								J	J	J	J	J	P	P	Q						
0.027 273																																											
0.033 333							C	C	C	C	C			G	G	G	G	J	J	J	J										J	J	J	J	J	Q	Q	Q					
0.039 393																																											
0.047 473							C	C	C	C	C			G	G	G	G	J	J	J	J										J	J	J	J	J	Q	Q	Q					
0.068 683							C	C	C	C	E			G	G	G	G	J	J	J	J										J	J	J	J	J	P	Q	Q					
0.082 823																																											
0.1 104		A					C	C	C	C	E			G	G	G	G	J	J	J	J									J	J	J	J	J	P	Q	Q						
0.12 124																																											
0.15 154														G	G	G	J	J	J	J											N	N	N	N	P		K	K	K	K	Q	Q	Q
0.22 224							C	C	C	C				G	G	J	J	J	J	J											N	N	N	N	P		K	K	K	K	Q	Q	Q
0.33 334														J	J	J	J	J	J	J											P	P	P	P	P		K	K	K	K	N	Q	
0.47 474							C	C						J	J	J	J	J	J	J											P	P	P	P	P		M	M	M	M	X	X	
0.68 684														J	J	J	J	J	J	J											P	P	P			M	M	M	M	X	X		
1.0 105							C							J	J	J	J	K												P	P	P	P		M	M	M	M	X	X			
2.2 225														J	J	K															P	P	P	P		M	M	M	M	X	X		
4.7 475														K																	P	P	P			X	X	X	Z				
10 106																															P	P	P			X	X	X	X				
22 226																																											
47 476																																											
100 107																																											
WVDC	16		6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	500					

Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
	PAPER						EMBOSSED							


NOTE: Contact factory for non-specified capacitance values
 *EIA 01005
 **Contact Factory for Specifications

X7R Dielectric Capacitance Range



PREFERRED SIZES ARE SHADED

SIZE	1210							1812					1825			2220					2225			
	Reflow Only Paper/Embossed							Reflow Only All Embossed					Reflow Only All Embossed			Reflow Only All Embossed					Reflow Only All Embossed			
(L) Length	3.30 ± 0.4 (0.130 ± 0.016)							4.50 ± 0.40 (0.177 ± 0.016)					4.50 ± 0.40 (0.177 ± 0.016)			5.70 ± 0.50 (0.224 ± 0.020)					5.70 ± 0.40 (0.224 ± 0.016)			
(W) Width	2.50 ± 0.30 (0.098 ± 0.012)							3.20 ± 0.40 (0.126 ± 0.016)					6.40 ± 0.40 (0.252 ± 0.016)			5.00 ± 0.40 (0.197 ± 0.016)					6.30 ± 0.40 (0.248 ± 0.016)			
(t) Terminal	0.50 ± 0.25 (0.020 ± 0.010)							0.61 ± 0.36 (0.024 ± 0.014)					0.61 ± 0.36 (0.024 ± 0.014)			0.64 ± 0.39 (0.025 ± 0.015)					0.64 ± 0.39 (0.025 ± 0.015)			
WVDC	10	16	25	50	100	200	500	16	25	50	100	200	500	50	100	200	25	50	100	200	500	50	100	200
Cap	100	101																						
(pF)	150	151																						
	220	221																						
	330	331																						
	470	471																						
	680	681																						
	1000	102																						
	1500	152																						
	2200	222																						
	3300	332																						
	4700	472																						
	6800	682																						
Cap	0.01	103																						
(µF)	0.015	153																						
	0.022	223																						
	0.033	333																						
	0.047	473																						
	0.068	683																						
	0.1	104																						
	0.15	154																						
	0.22	224																						
	0.33	334																						
	0.47	474																						
	0.68	684																						
	1.0	105																						
	1.5	155																						
	2.2	225																						
	3.3	335																						
	4.7	475																						
	10	106																						
	22	226																						
	47	476																						
	100	107																						
WVDC	10	16	25	50	100	200	500	16	25	50	100	200	500	50	100	200	25	50	100	200	500	50	100	200
SIZE	1210							1812					1825			2220					2225			



Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z	7
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)	3.30 (0.130)
	PAPER						EMBOSSED								

NOTE: Contact factory for non-specified capacitance values

Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

[AVX:](#)

[1206CC472KBT9A](#) [06031C103KA76N](#) [06035C273K3T2A](#) [06035C273K3T4A](#) [08051C223KAT4H](#)
[1206CA681MAJ1A](#) [08051C153KAT4H](#) [08051C222KAT4H](#) [06031C103MA76N](#) [1812YC335KA72Q](#) [08051C561JAT4H](#)
[08052C102JAT4H](#) [08052C561JAT4H](#) [12065C392KHT1A](#) [05045C103KA79A](#) [08055C104KAJ9A](#) [08051X471KSJME](#)
[12065C822KHT1A](#) [12065C393KHT1A](#) [0805ZC105MA76N](#) [0201YC681K](#) [05045C103KAT1A](#) [08055C104KH76A](#)
[12065C273KHT1A](#) [0805ZC105K3T4A](#) [12105X104KSJ9A](#) [08055X183KSJME](#) [0805ZC105KA76N](#) [08052C223KA76N](#)
[08051X392KSTME\500](#) [08053C104KGT1A](#) [0805ZC105JAJ9A](#) [12065C683KHT1A](#) [05045C102KA11A](#)
[08051X102KSJME](#) [08051X102KSJME\1K](#) [12065C682KHT1A](#) [08053C104KGT6A](#) [08051X472KSTME\500](#)
[0201YC471K](#) [1812YA104FBT1A](#) [06033C103KA76N](#) [22205C105KAJ9A](#) [0603YC104KAT4H](#) [18122C104KAJ9A](#)
[06035C103MA76N](#) [22201C105KAJ9A](#) [22207C224MAZ1A](#) [18255X474KSJ9A](#) [22251E225ZA1M6](#) [1206YC105MA76N](#)
[0603YC103MA76N](#) [0603YC103KA76N](#) [0603YC105KA76N](#) [0603YC273K3T4A](#) [06035C104KA76N](#)
[12063C564KA76N](#) [12063C105JAJ9A](#) [06031C103JA76N](#) [18121C104KAJ9A](#) [22251E225ZA116](#) [12061C102KAT4H](#)
[08051X121KSJ9A](#) [12061X103KSJME\1K](#) [05045C332JA16A](#) [05045C391KAT1A](#) [18125X104KSJ9A](#)
[08051X471KSJ1A](#) [12061X822KSJME\1K](#) [05045C221KAT1A](#) [05045C681KA11A](#) [05045C562KAT1A](#)
[08055X472KSJ9A](#) [05045C472JA19A\H](#) [08055X103KS19A](#) [05045C103KA76A\100](#) [05045C561KAT1A](#)
[05045C472MAT1A](#) [05045C101KA79A](#) [12105X104MSJ1A](#) [12061X103KSJ9A](#) [05045C103JAT1A](#) [05045C682JA19A\H](#)
[05045C103MA71A](#) [12105X473KSJME\1K](#) [05045C103MA79A](#) [05045C222JAT1A](#) [05045C103KA11A](#)
[05045C122JAT9A](#) [05045C152JHT6A](#) [12105X104MSJME](#) [08051X222KSJ9A](#) [08051X122KSJME\1K](#)
[08051X102KS1WE](#) [05045C222JA16A](#) [12105X104MSJ9A](#) [05045C332KAT1A](#) [05045C392JA16A\H](#)
[12105X104KS19A](#) [05045C152MA79A](#)